

Synthesis, characterization and antimicrobial activity of ZnS nanoparticles

Brenda Kwamboka, Wesley Omwoyo*, Nathan Oyaro

Department of Physical Sciences, Maasai Mara University, P.O. Box 861-20500, Narok, Kenya.
brndkwmbk13@gmail.com¹, wesleyomwoyo@mmarau.ac.ke², oyarokema@yahoo.com³

Abstract

Background/Objectives: Efforts have been put in the synthesizing of the ZnS nanomaterials in order to reduce dimensions for high quantum efficiencies. The objective of this study was to synthesize ZnS nanoparticles, characterize them and test for antibacterial activities.

Methods/Statistical analysis: The ZnS nanoparticles were synthesized with and without CTAB capping agent and characterized using affinity FTIR and UV-Visible spectrophotometer. The disc diffusion method was used to study the antibacterial activity of the synthesized ZnS nanoparticles. *Streptococcus aureus*, *Pseudomonas aeruginosa*, *Escherichia coli* and *Candida albicans* were used as model test strains.

Findings: The characterized peaks for ZnS stretching were absorbed at 354cm^{-3} and 964cm^{-3} for the capped ZnS. The uncapped ZnS had characteristic peaks stretching recorded at 360cm^{-3} and 1116cm^{-3} , 1255cm^{-3} and 1313cm^{-1} . The UV-Vis showed a blue shift as the maximum absorbance was observed at 310 nm.

Improvements/Applications: The ZnS nanoparticles were tested against oral pathogens and were found to exhibit anti-bacterial and anti-fungal activity.

Keywords: Nanoparticles, capping, absorbance, pathogens, anti-bacterial

1. Introduction

Nanotechnology is the design, characterization and application of nanomaterials and these include group II-VI of inorganic semiconductor such as ZnS, CdSe and ZnSe. These groups of nanomaterials have been found to be versatile materials because of their use in optoelectronic devices due to varied band gap as a function of the nanoparticle [1]. ZnS has been studied widely due to its wide applications in such areas as UV-diodes, phosphors in flat-panel displays and in photo catalysis [1, 2], sensors [2] and bio-devices [3]. ZnS nanocrystals doped with other metals in its application in photoluminescence is very complicated. This is so because small particles have larger surface to volume ratio and are more likely to access carriers for photoluminescence [4]. The application of ZnS in photochemical degradation is due to its higher resistance which is able to a part of the solar radiation that is carcinogenic and also to its low cost [5].

In recent years a lot of effort has been put in the synthesizing of the ZnS nanomaterials in an effort to reduce dimensions in the size of the circuits of electronic devices which are expected to have high quantum efficiencies due to their increased oscillatory strengths as a result of quantum confinement effects [4, 5]. The value of Bohr radius of the exciton in the bulk material has provided a threshold for occurrence of quantum effects [6]. ZnS nanoparticles have been prepared using many techniques such as soft chemical method [7], Chemical precipitation [8], sol-gel method [9], Co-precipitation [10], microwave irradiation method [7, 11] and colloidal micro emulsion [12]. In the present study the ZnS is synthesized without a capping agent and with a capping agent CTAB and its characteristics determined using FTIR and UV-Vis Spectrophotometer and its microbial activities using oral pathogens.

2. Materials and methods

2.1. Preparation of ZnCl₂ solution


12 mL of hexane, 3 mL of 1-pentanol and 0.6mg of CTAB were mixed together and continuously stirred and finally mixed with 0.6 gm of 0.012 M ZnCl₂.

2.2. Preparation of Na₂S solution

12 mL of hexane, 3 mL of 1-pentanol and 0.6 mg of CTAB were mixed together and continuously stirred and finally mixed with 0.6 ml of 0.012 M of Na₂S.

2.3. Preparation of ZnS nanoparticles in the presence of CTAB

This was done by mixing the ZnCl₂ solution and Na₂S solution as shown seen the equation below:



Zinc sulphide nanoparticles were also prepared in the absence of CTAB.

2.4. Characterization of the prepared ZnS nanoparticles

Fourier transform infrared spectroscopy (FTIR) was also used to determine the functional groups present on the surface of the nanoparticle while the absorption spectra was observed using the UV-VIS spectra within the range of 290-990.

2.5. Antimicrobial activity of the synthesized nanoparticles

The disc diffusion method was used to study the antibacterial activity of the synthesized ZnS nanoparticles. *Streptococcus aureus*, *Pseudomonas aeruginosa*, *Escherichia coli* and *Candida albicans* were used as model test strains. This method involves the inoculation filter paper discs with the synthesized ZnS nanoparticles and placed the discs in an agar plate which had been inoculated with specific organism. The plate was then incubated at 35° C for 24 hours. The inoculated discs created a zone of organism inhibition as it spread through the agar and this indicated the antimicrobial activity. Then the inhibition zone was measured.

3. Results and Discussions

3.1. Surface morphology of ZnS nanoparticles

The characteristic peaks of ZnS nanoparticles capped with CTAB (Figure 1) were recorded from 300-4000 cm⁻¹ using FTIR. Pure CTAB stretching vibrations of -CH₂ were observed at 2846.93cm⁻¹ and 2916.37 cm⁻¹. ZnS was not oxidized to zinc oxide which was indicated by the absence of peaks between 420-460 cm⁻¹ as was suggested by [13]. The Zinc and sulphide stretching are observed strongly at 354cm⁻¹ was also reported by [14]. ZnS peaks appeared at 964cm⁻¹ this was also reported by [15, 16, 17]. The peak at 671cm⁻¹ is ZnS band corresponding to sulphide and this was in line with what was reported by [18]. The peaks between 2900 - 3200cm⁻¹ are due to water absorption at the surface of the ZnS nanoparticles which indicate O-H stretching according to [19].

The FTIR spectroscopy in figure 2 shows bands of ZnS nanoparticle recorded from 300-4000cm⁻¹. The zinc and sulphide stretching were observed strongly at 360cm⁻¹ and this agrees with that reported by [14]. ZnS peaks appeared at 1116cm⁻¹ as was also reported by [16, 17, 20]. Major peaks can be observed at 1255cm⁻¹ and 1313cm⁻¹ indicating ZnS nanoparticle stretching as was also suggested by [20, 21]. The peaks between 2900 -3200cm⁻¹ are due to water absorption at the surface of the ZnS nanoparticles which indicate O-H stretching and this agrees with what was reported by [19].

From figure 3 shows UV-VIS spectra of zinc sulphide nanoparticles recorded in the range of 290- 990nm. The absorption edge spectrum appeared at 310nm which agreed with what was reported by [18, 22, 23]. This indicates that the absorption edge band is blue shifted since the bulk ZnS spectrum appears at 327nm as reported by [18]. Absorption at the wavelength corresponding to band gap energy arises due to optical excitation of electrons across the band gap and quantum effect causes the absorption spectra of ZnS to be towards the longer wavelength. This can be explained by the quantum size effect of semiconductor nanoparticles in their electronic structure, which originates from electron hole confinement in a small volume as reported by [23].

Figure 1. ZnS nanoparticles with CTAB as capping agent




Figure 2. ZnS nanoparticles without CTAB capping agent





Figure 3. UV-VIS spectra of ZnS nanoparticles at two different concentrations



3.2. Antimicrobial activity of the ZnS nanoparticles

The antimicrobial activity was studied against the oral pathogens *Staphylococcus aureus*, *Escherichia coli*, *Pseudomonas aeruginosa* and *Candida albicans*. The inhibition zone was measured around the well with ZnS nanoparticles with the CTAB as capping agent in millimeters against the test organism. The largest inhibition zone was measured against *E. coli* $17.50 \pm 0.03\text{mm}$ and *Staphylococcus aureus* had an inhibition zone of 10.30 ± 0.50 , (Figure 4).

Pseudomonas aeruginosa had an inhibition zone of $14.30 \pm 0.57\text{mm}$ and *Candida albicans* had inhibition zone of $9.55 \pm 0.50\text{mm}$ (Figure 5). For ZnS without the capping agent, the largest inhibition zone was measured against *E. coli* had an inhibition zone of $12.15 \pm 0.16\text{mm}$ and *Pseudomonas aeruginosa* had inhibition zone of $8.40 \pm 0.90\text{mm}$ while *Staphylococcus aureus* had an inhibition zone of $7.60 \pm 0.50\text{mm}$ and finally the *Candida albicans* had inhibition zone of $6.98 \pm 0.95\text{mm}$ (Table 1). The results demonstrate that the antimicrobial activities are due to the ZnS nanoparticles impregnated and surrounded by bacterial cell.


Table 1. Zone of inhibition in mm of ZnS Nanoparticle against oral pathogens

Type of Compound	Zone of inhibition(diameter in mm)			
	<i>C. albicans</i>	<i>S. aureus</i>	<i>P. aeruginosa</i>	<i>E. coli</i>
ZnS with CTAB	9.55 ± 0.50	10.30 ± 0.50	14.30 ± 0.57	17.50 ± 0.50
ZnS without CTAB	6.98 ± 0.95	7.60 ± 0.50	8.40 ± 0.90	12.15 ± 0.16

Figure 4. ZnS zone of inhibition against *S. aureus* (a) and *E. coli* (b)



Figure 5. ZnS zone of inhibition against *P. aeruginosa* (c) and *C. albicans* (d)



The antimicrobial activity of ZnS was stronger in CTAB than in uncapped ZnS nanoparticles this could be attributed to the interaction between the ZnS nanoparticles and CTAB material in the nanocomposite. The increased antimicrobial could be due to the small size of the ZnS and CTAB and the microorganism will take up the ZnS/CTAB and the antimicrobial activities are considerable for the low concentration and this is in agreement with the reported case on ZnS/A-FA by [24]. These results indicate zinc sulphide both capped and uncapped can be used as an antimicrobial agent against antibacterial and antifungal infections in various industrial applications and agricultural practices.

The inhibitory zone was largest by gram negative, gram positive and *Candida albicans*. In comparison of results highest antimicrobial activity was shown by the gram negative (*Escherichia coli*, *pseudomonas aureginosa*) than the gram positive (*Staphylococcus aureus*) this was in agreement with that reported by [25, 26]. This could be attributed to the cell wall nature of the oral pathogens. The can be used to explain the inhibitory activity exhibited by gram positive and gram negative bacteria. The gram positive bacteria have thick cell walls made up of complex linear polysaccharide chains; hence it is difficult for nanoparticles to penetrate the cell wall, while gram negative bacteria cell wall has small thickness thus allowing the nanoparticles to penetrate. The ZnS nanoparticles discharge ions which react with thiol groups in the protein cell membrane and disrupt the cell functions and finally the microorganism dies this has been reported by [27, 28, 29]. Nutrients are carried by these proteins into the cell membrane according to [30].

4. Conclusion

Zinc sulphide nanoparticles were synthesized and characterization was done by UV-VIS spectrophotometer, FTIR. Inhibitory activity of the zinc sulphide nanoparticles was tested against oral pathogens (*Staphylococcus aureus*, *Escherichia coli*, and *Pseudomonas aeruginosa* and *Candida albicans*) using the disc diffusion method and were found to have good antimicrobial activity. ZnS solution in solvent and capped zinc sulphide showed a higher inhibitory effect against Gram negative bacteria as compared to gram positive bacteria and had *Candida albicans* had the least inhibition zone. This clearly shows that capped and uncapped zinc sulphide can be used as an antimicrobial agent against antibacterial, antifungal infections, in various industrial applications and agricultural practices.

5. Acknowledgement

The authors would like to sincerely thank Maasai Mara University for providing the chemicals to support this study.

6. References

1. M. Jayalakshmi, M.M. Rao. Synthesis of zinc sulphide nanoparticles by thiourea hydrolysis and their characterization for electrochemical capacitor applications, *Journal of Power sources*. 2006; 157(1), 624-629.
2. J. M. Costa-Fernández, R. Pereiro, A. Sanz-medel. The use of luminescent quantum dots for optical sensing, *trends Anal. Chem.* 2006; 25, 207-218.
3. Lin, Su. Photoluminescence of Cu: ZnS, Ag: ZnS and Au: ZnS nanoparticle applied in Bio-Led, *Applied Physics*. 2013; 113, 351-359.
4. H. C. Ong, RPH Chang, optical constants of wurtzite ZnS thin films determined by spectroscopic ellipsometry. *Applied Physics Letter*. 2001; 79; 3612-3614.
5. Sobia Dilpazir, Muhammand Siddiq and Azhar Iqbal. Synthesis of zinc Sulphide nanostructures by co-precipitation: Effects of Doping on Electro-optical properties, *Kenkyu Journal of Nanotechnology and Nanoscience*, 2015; 1(2), 1-11.
6. Lai C-H, Lu M-Y, Chen L-J. Metal sulphide nanostructures: synthesis, properties and applications in energy conversion and storage, *Journal of matter, Chem.* 2012; 22:19- 30.
7. K. P. Tiwary, Sh. K. Choubey, K. Sharmac. Structural and Optical properties of ZnS nanoparticles synthesized by microwave irradiation method, *Chalcogenide letters*, 2013; 10, 319-323.
8. R. Zhang, Y. Liu., S. Sun. Synthesis and characterization of high quality colloidal Mn²⁺ dopZnS nanoparticles optical material, *Elsevier*. 2012; 34, 1788-1794.
9. H. D. Duong, J. Il Rhee. Enhancement of the sensitivity of a quantum dot-based fibre optic temperature sensor using the Sol-Gel technique. *Sensor and Actuators B chemical*, 2008; 134, 423-426.
10. L. S. Devi, K. N. Devi, B. I. Sharma, H. N.Sharma. Effect of Mn²⁺ doping on structural, morphological and optical properties of ZnS nanoparticles by chemical co-precipitation method. *Applied Physics*, 2014; 6, 6-14.
11. Tiwary, K. P., Choubey, Sh. K., K. Sharmac,. Structural and Optical properties of ZnS nanoparticles synthesized by microwave irradiation method II, *Chalcogenide letters*, 2013; 10, 319-323.
12. H. G. Manyar, P. Iliad, L. Bertinetti, S. Coluccia, Berlier,. Structural and spectroscopic investigation of ZnS nanoparticles grown in quaternary Reverse Micelles. *Journal of Colloidal and Interface Science*, 2011; 354, 511-516.
13. She Yuan-yuan, YANG Juan, QIU Ke-qiang. Synthesis of ZnS nanoparticles by solid-liquid chemical reaction with ZnO and NaS under ultrasonic, *Transactions of nonferrous metals society of China*. 2010; 20, 211- 215.
14. S. Aneeqa, A. S. Saadat, A. Salamat. Fabrication and Characterization of CdS Nanoparticles Annealed by using Different Radiations, *World Academy of Science Engineering and Technology*. 2010; 69, 82-89.
15. G. Navendu, P. Sen. Water-induced stabilization of ZnS nanoparticles, *Solid State Communications*. 2004; 132(11), 791-794
16. B. S. Devi, R. Raveendran, A. V. Vaidyan. Synthesis and characterization of Mn²⁺- doped ZnS nanoparticles. *Pramana Journal of Physics*. 2007; 68, 679.
17. M. Kuppayee, G. K. Vanathi Nachiyar, V. Ramasamy. Synthesis and characterization of Cu²⁺ doped ZnS nanoparticles using TOPO and SHMP as capping agents, *Applied surface Science*. 257, 2011; 6779-6786.

18. M. R. Bodke, Y. Purushotham, B. N. Dole. Crystallographic and optical studies on Cr doped ZnS nanocrystals, *Ceramica*. 2014; 60(355), 425-428.
19. K. Namakoto. Infrared and Raman Spectra of inorganic and coordination compounds, 5th (edn). John Wiley, New York. 1997.
20. M. Criado, A. Fernández-Jime'nez, A. Palomo. Alkali activation of fly ash: Effect of the SiO₂/Na₂O ratio: Part I: FTIR study Microporous and Mesoporous materials, 2007; 106(1-3), 180-191.
21. K. Swarup, M. Nillohit, M. Anup, A. Bibhutoh, K. Basudeb. Synthesis of nanocrystalline and mesoporous zinc sulphide from a single precursor Zn (SOCCH₃)₂Lut₂ complex, *Journal of Physics and chemistry of solids*. 2011; 72, 784-788.
22. W. Zhang, H. Hu. Synthesis and properties of transition metals and rare earth metals doped ZnS nanoparticles, *Optical Materials*. 2006; 28, 36-50.
23. I. Parvaneh, S. Samira, N. Mohsen, N. Mohsen. Characterization of ZnS nanoparticles synthesized by coprecipitation method, *Chinese Physics B*. 2015; 24(4), 1-4.
24. K. Kalyanaraman, S. Vaithilingam. Photo degradation and antibacterial studies of ZnS enwrapped fly ash nanocomposite for multipurpose industrial applications, *RSC Advances*. 2015; 5, 47766-47777
25. Y. Mamta, S. Ali, O. P. Yadav. Distinct anti-microbial effects of synthesized ZnS, Ag-N co-doped ZnS and ZnS-Fe₂O₃ composite nanoparticles against some pathogenic bacterial strains, Pelagia Research Library, Der Chemica Sinica, 2014; 5(6), 34-41.
26. M. A. Iftikhar, M. I. Isam, F. A. Entissar, A. Qayes. A. Structural and Characteristics of Manganese Doped Zinc Sulfide Nanoparticles and Its Antibacterial Effect against Gram-Positive and Gram-Negative Bacteria, *Open Journal of Biophysics*. 2016; 6, 1- 9.
27. C. Malarkodi, S. Rajeshkumar, Paulkumar, M. K. Vanaja, G. Gnanajobitha, G. Annadurai. Biosynthesis and Antimicrobial Activity of Semiconductor Nanoparticles against Oral Pathogens, *Bioinorganic Chemistry and Applications*, 2014, Article ID 347167, 1-10.
28. J. S. Kim, E. Kuk, K. N. Yu, J.H. Kim, S. J. Park, H.J. Lee, S. H. Kim, Y.K. Park, Y. H. Park, C. Y. Hwang, Y. K. Kim, Y. S. Lee, D. H. Jeong, M.H. Cho. Antimicrobial effects of silver nanoparticles, *Nanomedicine*, 2007; 3, 95-101.
29. M. Vanaja, S. Rajeshkumar, K. Paulkumar, G. Gnanajobitha, C. Malarkodi, G. Annadurai. Phytosynthesis and characterization of silver nanoparticles using stem extract of *Coleus aromaticus*, *International Journal of Materials and Biomaterials Applications*, 2013; 3(1), 1-4.
30. M. Shukla, S. Kumari, S. Shukla, R.K. Shukla. Potent antibacterial activity of nano CdO synthesized via microemulsion scheme, *Journal of Materials and Environmental Science*. 2012; 3(4), 678-685.

The Publication fee is defrayed by Indian Society for Education and Environment (iSee). www.iseeadyar.org

Citation:

Brenda Kwamboka, Wesley Omwoyo, Nathan Oyaro. *Synthesis, characterization and antimicrobial activity of ZnS nanoparticles*. *Indian Journal of Nanoscience*. 2016; 4(2), September.